



I.D.		O.D.		working pressure		bursting pressure (theoretical)		weight (nominal)		bending radius	
mm	inch	mm	inch	atm	psi	atm	psi	kg/m	lbs/ft	mm	inch
19	3/4	32	1-1/4	20	295	130	1910	1.00	0.67	90	3-1/2
25	1	38	1-1/2	20	295	110	1620	1.28	0.86	120	4-3/4
32	1-1/4	46	1-13/16	20	295	90	1320	1.75	1.18	150	6
38	1-1/2	52	2-1/16	15	220	80	1180	1.96	1.32	190	7-1/2
51	2	67	2-5/8	15	220	60	880	2.86	1.92	250	10
63,5	2-1/2	78	3-1/16	10	150	50	740	3.45	2.32	330	13
76	3	93	3-21/32	10	150	43	630	4.71	3.17	400	16
90	3-1/2	107	4-7/32	10	150	40	590	5.48	3.68	480	19
102	4	125,5	4-15/16	10	150	40	590	7.32	4.92	560	22
127	5	150,5	5-15/16	10	150	40	590	9.85	6.62	730	29
152	6	179	7-1/16	10	150	40	590	12.40	8.33	900	36

other sizes and pressure ratings available on request

EN Asphalt and tar hose, wire reinforced

Standards: EN 13482:2001.

Application: hardwall hose designed for the loading and unloading of hot asphalt and tar on tank trucks, tank wagons, and dock service.

Temperature: from -15°C (+5°F) to +200°C (+392°F).

Construction

Tube: black, smooth, synthetic rubber.

Reinforcement: plies of steel wire cord plus helix wire.

Cover: black, smooth (wrapped finish), synthetic rubber, weathering, ozone, abrasion, asphalt, and oil resistant.

Branding: continuous yellow stripe "IVG - EN 13482:2001 - Type 2 SB/B/I.D.-15 BAR - 200°C - quarter and year of production /ASPHALT and TAR".

